

Overprinting varnishes

UV Vernice Rilievo 1303: UV overprinting varnish ideal for high built prints (brail effect). This product should be applied by screen and due to its high viscosity it will result high thickness glossy prints. Very fast drying and absolutely not yellowing also after long outdoor exposure.

UV Label Trasparente 736: UV overprinting varnish with mat finish to be printed by flat screen machinery. This product can be used as transparent base for UV label colours. Very fast drying properties, accepts without problems hot stamping process.

UV Varnish Flexo Lucida Sp 2801: UV overprinting varnish to be applied by Flexo machinery with high glossy finish. All our Flexo varnishes do not contain Benzofenone and ITX. This product should be applied by flexo and it can be dried between 30 to 130 Mt/min (we suggest to apply the product by Anilox 160 lines/cm with a deposit of around 7.5 cm³/mq). This varnish accepts without problem hot stamping process and thermal transfer.

UV Varnish Flexo Opaca Sp 2501: UV overprinting varnish to be applied by Flexo machinery with mat finish, its glossy grade is between 10 to 20 depending on the substrate. It does not contain Benzofenone and ITX.

This product is very fast in drying and could be dried between 30 to 150 Mt/min, we suggest to apply the product by Anilox 160 lines/cm with a deposit of around 7.5 cm³/mq.

This varnish accepts without problem hot stamping process and thermal transfer.

